

THE 67TH INTERNATIONAL



OPEN READINGS

CONFERENCE FOR STUDENTS OF PHYSICS AND NATURAL SCIENCES

**BOOK OF
ABSTRACTS**

2024



Vilnius
University

VILNIUS UNIVERSITY PRESS

Editors:

Martynas Keršys
Rimantas Naina
Vincentas Adomaitis
Emilijus Maskvytis

Cover and Interior Design:

Goda Grybauskaitė

Vilnius University Press
9 Saulėtekio Av., III Building, LT-10222 Vilnius
info@leidykla.vu.lt, www.leidykla.vu.lt/en/
www.knygynas.vu.lt, www.journals.vu.lt

Bibliographic information is available
on the Lithuanian Integral Library Information System (LIBIS) portal www.ibiblioteka.lt
ISBN 978-609-07-1051-7 (PDF)

© Vilnius University, 2024

INVESTIGATION OF GRAPHENE/POLYPYRROLE COMPOSITES AND THEIR APPLICATION IN ELECTROCHEMICAL DOPAMINE SENSORS

Gintarė Rimkutė¹, Rasa Pauliukaitė², Gediminas Niaura², Jurgis Barkauskas¹, Justina Gaidukevič^{1,2}

¹Faculty of Chemistry and Geosciences, Vilnius University, Vilnius, Lithuania

²Center for Physical Sciences and Technology (FTMC), Vilnius, Lithuania
gintare.rimkute@chgf.vu.lt

The global sensor market is proliferating every year and is expected to reach \$345.77 billion by 2028 [1]. However, several issues still prevent the widespread impact and application of electrochemical sensors. It is mainly related to the materials used in these devices, which often lack the sensitivity and selectivity required for the detection of target analytes [2]. For this reason, current research is often focused on nanostructured carbon materials, which have many unique properties, including high electrical conductivity, biocompatibility, enzyme mimicking activity, and can be easily obtained using low-cost preparation methods [3].

The purpose of this work was to produce graphene-polypyrrole (GP) composites, characterize them, and investigate their sensitivity in the non-enzymatic detection of dopamine (DA). Three different graphite precursors with grain sizes of $<50 \mu\text{m}$, ≥ 150 , $\leq 830 \mu\text{m}$ and $\leq 2000 \mu\text{m}$ were intercalated with sulfuric acid and thermally treated to obtain exfoliated graphite (EG). EG samples were further modified with conductive polymer polypyrrole. The acquired samples were characterized using SEM, XPS, and Raman spectroscopy techniques. Electrochemical investigations were conducted using differential pulse voltammetry (DPV). Additionally, the potential application of the prepared GP nanocomposites for highly sensitive non-enzymatic DA sensors was explored.

Structural analysis showed that the sample obtained from the medium-size graphite grains (GP_2) had the lowest number of defects ($ID/IG = 0.483$) and the highest elemental nitrogen content (5.12 at.%) with 15.16 at.% as graphitic-N, known to improve electrocatalytic activity. Electrochemical investigations demonstrated that all GP samples were prospective for DA sensing. However, the electrode modified with the GP_2 showed the best performance. The sensitivity of this sensor was $2180 \mu\text{A}\cdot\text{mM}^{-1}\cdot\text{cm}^{-2}$ and the limit of detection was 78 nM.

[1] I. O'Connell, S. Chevella, G.M. Salgado, D. O'Hare, Precision Voltage Sensing in Deep Sub-micron and Its Challenges, in: Analog Circuits for Machine Learning, Current/Voltage/Temperature Sensors, and High-Speed Communication, Springer International Publishing, 137–163 (2022).

[2] C. Ferrag, K. Kerman, Grand Challenges in Nanomaterial-Based Electrochemical Sensors, *Frontiers in Sensors*, 1 (2020).

[3] Y. He, C. Hu, Z. Li, C. Wu, Y. Zeng, C. Peng, Multifunctional carbon nanomaterials for diagnostic applications in infectious diseases and tumors, *Mater Today Bio*, 14 (2022).