

THE 67TH INTERNATIONAL



OPEN READINGS

CONFERENCE FOR STUDENTS OF PHYSICS AND NATURAL SCIENCES

**BOOK OF
ABSTRACTS** | **2024**



Vilnius
University

VILNIUS UNIVERSITY PRESS

Editors:

Martynas Keršys
Rimantas Naina
Vincentas Adomaitis
Emilijus Maskvytis

Cover and Interior Design:

Goda Grybauskaitė

Vilnius University Press
9 Saulėtekio Av., III Building, LT-10222 Vilnius
info@leidykla.vu.lt, www.leidykla.vu.lt/en/
www.knygynas.vu.lt, www.journals.vu.lt

Bibliographic information is available
on the Lithuanian Integral Library Information System (LIBIS) portal www.ibiblioteka.lt
ISBN 978-609-07-1051-7 (PDF)

© Vilnius University, 2024

NANO-PROCESSING BY FS-UVINTERFERENCE METHOD

Tadas Latvys¹, Darius Gailevičius¹, Dominyka Stonytė¹, Domas Paipulas¹, Vytautas Jukna¹

¹Laser Research Center, Faculty of Physics, Vilnius University, Vilnius LT-10223, Lithuania
tadas.latvys@ff.stud.vu.lt

Today material processing by ultrashort pulses in UV spectral domain allows us to achieve high precision and efficiency. However, in large-area surface patterning optical lithographic techniques [1] are still being used despite having limited selection of usable materials and requiring multiple processing steps, facilities and machines. Therefore, there is a demand for alternative methods such as fs-UV interference processing. This method can produce large areas of periodically arranged structures with a period close to the wavelength of the used fs-pulses. This ensures accurate and fast surface patterning without requiring additional preparation or post-processing.

Fs-UV interference method has a wide range of potential applications in photonics, nanotechnology, or biomedicine. Specifically, it can be utilized to produce functional surfaces that exhibit antireflective [2], antibacterial [3], or hydrophobic [4] properties.

In this presentation, we present our results for two-beam interference patterning using the third (343 nm) harmonic of an amplified Yb:KGW laser system, providing pulse durations of 240 fs. To achieve interference on the sample, a prototype machining head (Talbot interferometer) was constructed (Fig. 1a). This setup has many drawbacks when used with ultrashort pulses [5], thus a Kostenbauder matrix formalism [6] was employed to calculate optimal parameters for the alignment of the pulses. Consequently, homogeneous gratings with nanoscale feature sizes were fabricated on a silicon surface with periods of $\Lambda = 800$ nm (Fig. 1b). In addition, etching the gratings in a 1% KOH solution resulted in a 10-fold increase in structure height.

In summary, our study showcases the direct processing of centimeter-scale areas through an fs-UV interference method. The Talbot approach not only ensures ease of alignment and precise period control but also offers the advantage of having a compact configuration. Importantly, material removal can be controlled with nanoscale precision.




Fig. 1. (a) Talbot interferometer setup, (b) periodically patterned Si surface.